

Grade: Kostrate® EDGE ME
Injection Molding Grade

Typical Material Properties

Physical	Nominal Values (English)	Test
Specific Gravity	1.04	ASTM D792
Melt Flow	8.0 g/10 min	ASTM D1238
Food Contact Acceptable	21 CFR 177.1640	FDA
	21 CFR 174.5	FDA
Mechanical		
Tensile Strength @ Break	6000 psi	ASTM D638
Flexural Modulus	320,000 psi	ASTM D790
Flexural Strength @ Yield	9000 psi	ASTM D790
Tensile Strength @ Yield	5000 psi	ASTM D638
Elongation	120%	
Hardness	75 Shore D	
Impact		
Dart Drop	25 (in-lbf)	
Impact on 0.125 x2.5" disk		
Thermal		
HDT @ 66 psi-unannealed (.125 in.)	190 °F	ASTM D648
Mold Shrinkage		
Linear Flow	.003 - .006 in/in	ASTM D955
Optical		
Haze	1.0	ASTM D1003
Light Trans	91%	ASTM D1003

Additional: Dishwasher safe, FDA compliant. Please note to allow your part to come to room temperature as parts become more water clear and harder surface after a dwell time of 72 hours.

The information provided above is based upon typical values. Typical values are intended only as guides. Each customer is responsible for determining whether products and information in this document are appropriate for the customer's use. NO GUARANTEES OR WARRANTIES ARE EXPRESSED OR IMPLIED.

Grade: Kostrate® EDGE ME
Injection Molding Grade

Recommended Processing Guidelines

INJECTION MOLDING:

	Nominal Values (English)
Drying Temperature	No Drying needed
Drying Time	NA
Suggested Max Moisture	NA
Rear Temperature	350 to 360 °F
Middle Temperature	360 to 375 °F
Front Temperature	375 to 390 °F
Nozzle Temperature	370 to 390 °F
Processing (Melt) Temp	350 to 440 °F
Mold Temperature	60 to 100 °F
Back Pressure	50 to 200 psi
Screw Speed	40 to 80 rpm

The information provided above is based upon typical values. Typical values are intended only as guides. Each customer is responsible for determining whether products and information in this document are appropriate for the customer's use.
NO GUARANTEES OR WARRANTIES ARE EXPRESSED OR IMPLIED.